COPPERFIT Project: _______ / Contractor: ______ INDUSTRIES Architect: ______ / Contractor: ______ Engineer: _____ / Date: ______ www.copperfit.com

Heavy Duty No-Hub Coupling

The CFI Heavy Duty No-hub Coupling is designed and engineered to provide superior performance at a very competitive cost. The coupling meets or exceed the requirements of ASTM C1540 Uniform Plumbing Code (UPC). The gasket of the coupling is made from elastomeric compound that meets the ASTM C-564 standard, and the corrugated shield is made from type 304 stainless steel.

Material Specifications

Clamp: Type 304 AISI Stainless Steel Screw: Type 305 AISI Stainless Steel 5/16" hex head for 1-1/2"-8" Shield: Type 304 AISI 0.007" thick stainless steel Gasket: Made from high-quality elastomeric compound (ASTM C-564), the gasket feature multiple sealing beads under the clamp bands.

The coupling consists of an elastomeric gasket, Stainless steel shield, two or four clamps assembly. It is used join no hub cast iron pipe and fittings which are made to conform to the ASTM A888 standard.



| Heavy Duty No-Hub Coupling | | | | | |
|----------------------------|--------|------------------|-------|--------|--|
| Part# | Size | Number of straps | Width | Torque | |
| 60001 | 1-1/2" | 4 | 3 | 80 | |
| 60002 | 2″ | 4 | 3 | 80 | |
| 60003 | 3″ | 4 | 3 | 80 | |
| 60004 | 4″ | 4 | 3 | 80 | |
| 60006 | 6" | 6 | 4 | 80 | |
| 60008 | 8″ | 6 | 4 | 80 | |

| Test | GASKET PHYSICAL TEST MIN. OR MAX. REQUIREMENTS | ASTM METHOD |
|------------------------|---|----------------|
| Tensile Strength | 1500psi min. | D 412 |
| Elongation | 250 min. | D 412 |
| Durometer (Shore A) | 70 ±5 @ 76°F ±5°F | D 2240 |
| Accelerated Aging | 15% maximum tensile and 20% maximum elongation, 10 points maximum increase in hardness , all determinations after oven aging for 96 hours at 158°F | D 573 |
| Compression Set | 25% max. after 22 hours at 158°F | D 395 Method B |
| Oil Immersion | 80% max. volume change after immersion in IRM 903 for 70 hours at 212°F | D 471 |
| Ozone Cracking | No visible cracking at 2 times magnification of the gasket after 100 hours exposure in 1.5 ppm ozone concentration at 104°F. Testing and inspection to be on gasket which is loop mounted to give approximately 20% elongation of outer surface. | D 1149 |
| Tear Resistance | 150lbf/in. min. | D 624 |
| Water Absorption | ater Absorption 20% max. by weight after 7 days at 158°F | |